

Selection & Specification Data

Generic Type	Polyamido-Amine Epoxy
Description	Penetrating primer/sealer for use on concrete substrates and Carboline Pyrocrete Fireproofing products. It performs extremely well in sealing cementitious surfaces and is designed to receive a variety of different generic types of finish coats. Some recommended uses of 1340 include the use as a curing compound or form release agent. When applied to "green" concrete it will retard the escape of moisture during the cure period. It is also excellent for use as a form release coating on plywood or steel forms. Meets the requirements of ASTM C309 when applied at 5.0-10.0 mils (125-250 microns) wet.
Features	<ul style="list-style-type: none"> ▪ Exceptional wetting characteristics ▪ Low stress, highly flexible film ▪ Very high solids ▪ Low odor ▪ User-friendly brush & roller application ▪ VOC compliant to current AIM regulations ▪ Nuclear Service Level 1
Color	Clear Amber (0910)
Finish	Gloss
Primers	Self-priming. May be applied over most generic types of coatings.
Topcoats	Acrylics, Epoxies, Polyurethanes
Dry Film Thickness	1.0 - 2.0 mils (25 - 50 microns) DFT for most applications but can be applied up to 4.0 mils (100 microns) for sealing rough surfaces or shot-blasted concrete. When used as a curing and/or form release agent, it may be applied up to 10.0 mils (250 microns) wet.
Solids Content	By Volume: 98% ± 2%
Theoretical Coverage Rate	1572 mil ft ² (38.5 m ² /l at 25 microns) Allow for loss in mixing and application. Porous and irregular substrates like concrete/fireproofing coverage rates and should be taken into account.
VOC Values	As supplied: 0.2 lbs/gal (24 g/l) EPA Method 24: 0.8 lbs/gal (95 g/l) Thinned: 25 oz/gal w/ #76: 1.8 lbs./gal (214 g/l) These are nominal values.
Dry Temp. Resistance	Continuous: 175°F (79°C) Non-Continuous: 200°F (93°C)
Limitations	<ul style="list-style-type: none"> ▪ Epoxies lose gloss, discolor and eventually chalk in sunlight exposure. ▪ Do not use for immersion service.

Substrates & Surface Preparation

Concrete	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.
As a Curing Membrane	Pyrocote 1340 has been tested in accordance with ASTM C 309-98a Standard Specification for Liquid Membrane Forming Compounds for Curing Concrete and passes the requirements set forth in the standard. While 1340 may be applied to green concrete, generally additional coats or other coatings should not be applied until the concrete has cured 28 days at 75°F (24°C) and 50% R.H. or equivalent. Prior to topcoating we recommend that a test patch be applied to insure proper adhesion.
General	Concrete must be cured 28 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. Voids in concrete may require surfacing. Application prior to surfacing assures tight adhesion between concrete and surfacers or membranes. Compatibility with other coatings, surfacers and polyurethane membranes eliminates need for form release oils or curing oils.
Pyrocrete Fireproofing Products	Consult the appropriate Pyrocrete product data sheet for specific topcoating instructions.
Previously Painted Surfaces	Lightly sand or abrade to roughen and degloss the surface. Existing paint must attain a minimum 3B rating in accordance with ASTM D3359 "X-Scribe" adhesion test.

Application Equipment

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

General Guidelines:

Spray Application (General) Contact Carboline Technical Service for spray equipment and technique.

Brush & Roller (General) Avoid excessive re-brushing or re-rolling. Apply only enough material to wet the surface uniformly. Any puddles formed must be brushed out.

Brush Use a medium bristle brush.

Roller Use a medium or long-nap synthetic roller cover with phenolic core.

Mixing & Thinning

Mixing Power mix separately, then combine and power mix. DO NOT MIX PARTIAL KITS.

Ratio 1:1 Ratio (A to B)

Thinning Normally not required but may be thinned up to 25 oz/gal (20%) with Thinner #76. Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

Pot Life 45 minutes at 75°F (24°C). Pot life will be less at higher temperatures.

Cleanup & Safety

Cleanup Use Thinner #2 or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

Safety Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas.

Ventilation When used in enclosed areas and product is thinned, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator.

Caution This product exotherms at the end of its pot life. Any unused quantities will become extremely hot. The material begins to thicken at the end of its pot life, which is an indication of exotherm. Immediately spread out on an appropriate surface or add sand or other suitable heat sink to the unused material to reduce the severity of exotherm. Take appropriate precautions against breathing fumes. This product when thinned contains flammable solvents. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workmen should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

Application Conditions

Condition	Material	Surface	Ambient	Humidity
Normal	60°-80°F (16°-27°C)	60°-80°F (16°-27°C)	60°-80°F (16°-27°C)	0-80%
Minimum	60°F (16°C)	50°F (10°C)	50°F (10°C)	0%
Maximum	90°F (32°C)	130°F (54°C)	100°F (38°C)	90%

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel. Special application techniques may be required above or below normal application conditions.

Curing Schedule

Surface Temp. & 50% Relative Humidity	Dry to Topcoat or Handle	Maximum Recoat Time w/ Water Borne	Maximum Recoat Time w/ Solvent Borne	Final Cure
50°F (10°C)	24 Hours	14 Days	30 Days	9 Days
75°F (24°C)	12 Hours	14 Days	30 Days	6 Days
90°F (32°C)	6 Hours	7 Days	15 Days	3 Days

These times are based on a 1.0-2.0 mil (25-50 micron) dry film thickness. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. Excessive humidity or condensation on the surface during curing can interfere with the cure, can cause discoloration and may result in a surface haze. Any haze or blush must be removed by water washing before recoating. During high humidity conditions, it is recommended that the application be done while temperatures are increasing. If the maximum recoat time is exceeded, the surface must be abraded by sweep blasting or sanding before the application of additional coats.

Curing Schedule for Curing/Form Release Agent

Surface Temp. & 50% Relative Humidity	Dry to Topcoat or Handle	Final Cure
75°F (24°C)	5 Hours	6 Days

These times are based on 5.0-10.0 (125-250 microns) mils dry film thickness.

Packaging, Handling & Storage

Shipping Weight (Approximate)	<u>0.5 Gallon Kit</u> 6 lbs (3 kg)	<u>2 Gallon Kit</u> 22 lbs (10 kg)
Flash Point (Setaflash)	Part A: >205°F (96°C) Part B: >205°F (96°C)	
Storage Temperature & Humidity	40° - 110°F (4°-43°C) 0-90% Relative Humidity	Store indoors.
Shelf Life	Part A & B: Min. 36 months at 75°F (24°C)	

***Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.**



350 Hanley Industrial Court, St. Louis, MO 63144-1599
314/644-1000 314/644-4617 (fax) www.carboline.com

An **RPM** Company