

PRODUCT DESCRIPTION

PLASITE 4550 S is a 100% solids, flake filled, premium novolac epoxy coating designed for internal steel and concrete substrates. It is a two component system consisting of four-parts by volume of Part A resin and one part by volume of Part B hardener. It is applied by plural component or single component spray equipment, from a total thickness of 20-60 mils (500-1500 microns) in a single coat application for a variety of applications.

USES/APPLICATIONS (examples)

- Chemical Storage Tanks
- Wastewater Clarifiers
- Plating Vats
- Oil Storage Tanks
- Ethanol Storage Tanks
- Catwalks
- Concrete exposures in wastewater applications
- Pulp and Paper liquor tanks

PRODUCT ADVANTAGES

- High impact resistance
- Superior bondability to steel and concrete
- Resistance to a broad range of chemicals
- Can be applied up to 60 mils in one coat
- Can be sprayed using single component airless equipment

CHEMICAL RESISTANCE

PLASITE 4550 S is resistant to a broad range of chemicals such as fuels, salts, alkalis, some solvent, and many acids (including concentrated sulfuric acid).

COLORS

PLASITE 4550 S is offered in light gray, tile red and white.

PACKAGING

PLASITE 4550 S is available in one and five gallon units.

One gallon unit includes:

- 1 gallon (partial) can of Part A (resin)
- 1 quart can of 4500S/4550S Part B (hardener)

Five gallon unit includes:

- 5 gallon (partial) pail of Part A (resin)
- 1 gallon can of 4500S/4550S Part B (hardener)

FILM THICKNESS

Depends on service and condition of existing substrate, PLASITE 4550 S is typically applied at 20 mils in a single coat application.

COVERAGE

The theoretical coverage of PLASITE 4550 S is 1604 mil sq ft/gal. For estimating purposes, one gallon will cover 64 sq ft/gal at 20 mils (20% loss included).

THINNERS

NO THINNER IS RECOMMENDED

CLEANUP THINNER: Thinner #71

VOC CONTENT

| Color | VOC of Coating as Supplied (Determined Theoretically) | |
|----------|--|------|
| | Lbs./Gal. | g/L |
| Lt. Gray | 0.00 | 0.00 |

PHYSICAL CHARACTERISTICS

Tensile Strength.....7,500 psi (ASTM D-638)

Flexural Strength.....10,800 psi (ASTM D-790)

Flexural Modulus of Elasticity.....5.9 psi x 10⁶ (ASTM D-790)

Hardness.....75(ASTM D-2240 Shore D)

Weight per Mix.....10 lbs.

Shelf Life.....6 months

Pot-life.....@75°F/24°C: 45-60 minutes.

Cure Time (Approx.):

Dry To Touch.....@ 75°F/24°C: 12 hours

Firm.....@ 75°F/24°C: 24 hours

Cure for Immersion service (min 50°F/15°C)

Crude oil or aliphatic hydrocarbons..... @ 75°F/24°C: 36 hours

Most Chemical Service..... @ 75°F/24°C: 5 days

Flammability.....Nonflammable

Bond Strength.....1,700 psi

STORAGE CONDITIONS

Keep PLASITE 4550 S products tightly sealed in their original containers until ready for use. Store at 50-85°F/10-29°C, out of direct sunlight. Properly stored, PLASITE 4550 S Part A has a shelf life of 6 months; Part B, 24 months.

Proper jobsite storage of PLASITE 4550 S is essential to its performance. Follow these general procedures for storage at the jobsite:

Store components (Part A and Part B) unopened, in a dry place, at 50-85°F/10-29°C, out of direct sunlight, and protected from the elements. Keep away from heat and flame.

For the 24-48 hours just prior to use, narrow the storage temperature to 70-85°F/21-29°C to facilitate ease of mixing.

SUBSTRATE PREPARATION**Steel**

Immediately prior to application of the coating or lining, the steel substrate must be clean of all oil, grease, dirt, dust, mill scale, rust, flash rust, corrosion products, salts, solvents, chlorides, other chemicals, and existing coatings.

All welds must be smooth and continuous; no skip welds. All weld splatter, buckshot, laminations, and slivers must be removed and ground smooth; undercuts and pinholes must be ground smooth and filled with weld metal. All projections, sharp edges, high points and fillets must be ground smooth to a radius of at least 1/8 in and all corners must be likewise rounded.

All pitting, gouges, scratches, and other defects must be repaired either by welding or by filling with repair materials that are compatible with the coating or lining system and suitable for the intended service conditions.

All surfaces to be coated or lined must be readily accessible.

The steel must be blasted to a minimum near White Metal Finish (NACE No. 2, SSPC SP 10) with a 4 mil/100 micron dense, sharp anchor profile free of peening, as measured by ASTM D 4417.

Defects exposed by blasting must be repaired. Refer to Plasite Bulletin PA-3.

September 2006 replaces June 2006

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Carboline® and Plasite® are registered trademarks of Carboline Company.

PLASITE® 4550 S

Concrete

Immediately prior to application of coating, concrete substrate must be:

- Adequately cured (generally, at least 28 days; check with Carboline if concrete has cured less than 28 days).
- Structurally sound.
- Free of all dirt, dust, debris, oil, grease, fats, chemical contamination, salts, solvents, surface hardeners, incompatible curing compounds and form release agents, laitance and efflorescence.
- Concrete surface must be dry.

And must have:

- Tensile strength of at least 300 psi.
- pH in the range of 7 to 11.
- All fins, projections and splatter removed.
- All defects repaired using patching as described herein.
- Failed or otherwise incompatible old coatings removed.
- A surface texture similar to medium sandpaper (40 to 60 grit).

Refer to Carboline's separate document "Surface Preparation – Concrete" for further instruction in the preparation of concrete surfaces.

Locate all expansion joints, control joints, floor drains, equipment base plates, and mid-floor termination points. Handle them as per Carboline's separate document "Construction Details".

Degraded concrete on horizontal surfaces should be restored using Carboguard 510 Concrete Repair Mortar or specified restoration materials.

Honeycombs or any form voids in vertical surfaces must be filled. Use a putty made with Carboguard 510 Concrete Repair Mortar.

Concrete is a very porous material. As it warms during the day it expels air, or "outgasses". A coating applied while the concrete is outgassing likely will develop bubbles and pinholes.

To avoid this, the material should be applied when the temperature of the concrete is falling. Usually this is from late afternoon into the night. Stop applying the material well before dawn, so it has time to set up firm to the touch before outgassing begins. This may be anywhere from 1 to 6 hours, depending upon the weather conditions. In addition, it is a good idea to shade the work area from direct sunlight. Do not apply material when temperature will fall within 5°F/3°C of the dew point.

Priming may be required in situations where outgassing could be a problem. Consult Carboline for primer recommendations.

MASKING & PROTECTION

Mask or remove adjacent surfaces and equipment that are not to be lined. Once applied, PLASITE 4550 S is difficult to remove.

Protect nearby pumps, motors and other equipment from spent abrasive venting from the tank during blasting.

APPLICATION GUIDELINES

Before mixing and applying any material, make sure environmental conditions are satisfactory for application. Weather conditions, and especially dew point, should be constantly monitored in light of the work being done. Final blast cleaning and application of the lining system must only be performed when it is clear the temperature of the steel substrate will not fall within 5°F/3°C of the dew point. Dehumidification and/or temperature control may be necessary to meet this requirement. Use a surface thermometer to frequently monitor the temperature of the steel substrate.

EQUIPMENT

Single Component Airless Spray

All pumps and hoses must be in proper working order, clean and free of foreign matter. Use air motor with an air ratio of 45:1 or larger such as Graco "King" airless spray pump.

All filters should be removed from the pump. Use a 3/8 in. spray hose from pump to gun, not to exceed 100 in. It is best to bring the material directly to the gun body and not go through a tube in the handle.

The size of airless spray tip will depend on the area being sprayed, the viscosity, and the temperature of the materials. Use sizes from 0.019-0.035 inches. If using an inline filter, use a 60-mesh screen size.

The mixed material temperature should be 75-85°F/24-38°C for best spraying.

Note: Ambient temperature above 85°F/29°C will shorten pot life.

To prepare the material for spraying, mix Part A with a jiffy type mechanical mixer for two minutes, mix Part B until color is well blended, then mix Part A and Part B together for two minutes using the jiffy mixer.

When using a 45:1, set the mixed material under the pump (it is best to remove the siphon tube and pump directly from the bottom of the pump) and start spraying. The air pressure required will vary between 55-65 lbs. If using a 56:1, the siphon tube may remain attached.

When spraying is completed, solvent purge the lower unit and spray gun, then remove the bottom ball valve and clean thoroughly.

Plural Spray

Use a fixed ratio (4:1 by volume) plural component spray rig such as: Graco King Hydro-Cat (or equal) with heated hoppers, heated hoses to a mixer manifold through a static mixer to a 50 ft. whip hose followed by a silver gun (Binks 1M or equal) utilizing self-cleaning reverse "a" tips from 0.019 to 0.035 inches. See equipment specifications for more details.

Note: The "A" side should be at a minimum of 110°F/43°C and the "B" side at 90-100°F/32-38°C. This will ensure proper spraying of PLASITE 4550 S. Take care to prevent the mixed material from setting up in your hoses. For best results, keep your hoses as short as possible, purge them immediately if work is interrupted, keep them out of direct sunlight and insulated from hot surfaces.

APPLICATION

Mixing

For Touch-Up Only

We recommend using Jiffy type mixers for all mixing and stirring. When operating the mixer avoid plunging it up and down in the bucket. This can fold air into the resin, which may cause bubbles to form in the coating after it has been applied.

Individually stir each separate Part A and Part B component to a smooth, uniform consistency and color. Any sediment in the container must be thoroughly scraped up and redispersed.

Spray

Immediately before applying a spray coat, stripe all continuous welds and edges with a brush-coat to assure adequate protection of these areas.

All spray equipment should be clean and in proper working order. Contact Carboline's Technical Service Department for start-up and clean-up procedures. Adjust pressure to 50-70 psi and open the valves at the manifold and purge materials at the spray gun. Attach spray tip and begin to spray. Dependent upon tip size, each pass will be 8-14 mil/200-350 microns per pass. Apply material to specified thickness.

Apply criss-cross multi-passes, moving gun at a fairly rapid rate, maintaining a wet appearing film. Use a wet film thickness gauge to monitor film build.

Note: Force curing may be desirable in certain circumstances. Check with Carboline's Technical Service Department.

CURING

PLASITE 4550 S will be dry to the touch in 12 hours at 75°F/24°C and ready for most immersion services in 5 days at 75°F/24°C.

LINING REPAIR

Before any touch-up or recoat material can be applied, the first coat must be properly prepared for intercoat adhesion.

The first coat must be cured firm to the touch. Coating on floors must be able to support foot traffic.

Scrub the first coat with soap and water and thoroughly rinse and dry it.

If the first coat cures more than 24-hours, lightly sand or mechanically abrade the surface after scrubbing it down with soap and water.

September 2006 replaces June 2006

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Carboline® and Plasite® are registered trademarks of Carboline Company.

Any surface to be touched up or recoated should be protected. When the recoat material is applied, the surface must be dry and free of all dirt, dust, debris, oil, grease and other contamination.

INSPECTION

Degree of surface preparation shall conform to appropriate specifications as outlined in SURFACE PREPARATION section. Film thickness of each coat and total dry film thickness of the coating system shall be determined with a non-destructive magnetic gauge properly calibrated.

RECOMMENDATIONS

- Apply only on a clean, sound, properly prepared substrate.
- Minimum ambient or substrate temperature is 50°F/10°C, at the time of application. Optimal temperature is 75°F/24°C.
- Maximum ambient or substrate temperature is 100°F/38°C.
- Relative humidity should be between 0-90%.
- Substrate temperature should be 5°F/3°C above the dew point.
- Application and curing times are dependent upon ambient conditions. Consult Carboline's Technical Service Department if conditions are not within recommended guidelines.

PRECAUTIONS

- PLASITE Thinner #71 is recommended for clean up of the PLASITE 4550 material.
- Before handling and application of this material consult the MSDS sheets. As with any product, those handling PLASITE 4550 materials should employ proper safety practice. Hypersensitive persons should wear protective clothing, gloves, and use protective cream on any exposed areas.
- When PLASITE 4550 is used as a tank lining or in an enclosed area circulation should be used during and after the installation. Circulation can be discontinued once the material has cured. The ventilation equipment should be capable of preventing the solvent concentration from reaching the lower explosion level for the solvents used. The applicator should monitor the exposure levels or use MSHA/NIOSH approved air respirators.

NOTES

- Material Safety Data Sheets on PLASITE 4550 are available upon request.
- Specific information regarding the chemical resistance of PLASITE 4550 can be found by contacting Carboline's Technical Service Department.
- A staff of technical service engineers is available to assist with product application, or to answer questions related to Carboline products.
- Requests for technical literature or service can be made through local sales representatives and offices worldwide.



350 Hanley Industrial Court, St. Louis, MO 63144-1599
314/644-1000 314/644-4617 (fax) www.carboline.com

An **RPM** Company

September 2006 replaces June 2006

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Carboline® and Plasite® are registered trademarks of Carboline Company.